

## Technical Data Sheet

### PP OMILEN® P FIM T30 BK

**Product description:** composite of recycled polypropylene contain mineral filler (30%), intended for forming products by extrusion and injection mould. Available in black color.

**Application area:** automotive, household goods, building, furnishes industries, electrical and electronical.

Properties	Value	Unit	Condition	Standard	
<b>Rheological</b>					
MFR	<b>6</b>	g/10 min	230 °C; 2,16 kg	EN ISO 1133	
MVR	<b>7</b>	cm <sup>3</sup> /10 min	230 °C; 2,16 kg	EN ISO 1133	
<b>Mechanical</b>					
	<b>dry</b>	<b>cond.</b>			
Tensile stress at yield	<b>18</b>	-	MPa	5 mm/min	EN ISO 527
Elongation at break	<b>10</b>	-	%	5 mm/min	EN ISO 527
Tensile stress at break	<b>16</b>	-	MPa	5 mm/min	EN ISO 527
Flexural strength	-	-	MPa	mm/min	EN ISO 178
Tensile modulus	<b>500</b>	-	MPa	1 mm/min	EN ISO 527
Charpy notched	<b>11</b>	-	kJ/m <sup>2</sup>	4 J; V-2 mm	EN ISO 179
Charpy unnotched	<b>41</b>	-	kJ/m <sup>2</sup>	15 J	EN ISO 179
Izod notched	-	-	kJ/m <sup>2</sup>	J; V-2,5 mm	EN ISO 180
Izod unnotched	-	-	kJ/m <sup>2</sup>	J	EN ISO 179
<b>Physical</b>					
Density	<b>1,04</b>		g/cm <sup>3</sup>	23 °C	EN ISO 1183-1
Ash content	<b>30</b>		%	650 °C	EN ISO 3451
<b>Thermal</b>					
Flame rating	-		Class	127x12,7x3,2 mm	UL 94

Processing parameters		
Parameter	Condition	Unit
Drying temperature	80-100	°C
Drying time	4	h
Suggested max moisture drying	0,2	%
Processing (melt) temp	200-250	°C
Mold temperature	20-80	°C

F-11.1\_i-26 – Technical Data Sheet

These studies are drawn from a random sample. An overall picture of the properties of the material. Individual parts of the material may slightly differ from the values in the table. Slight deviations from these results do not give rise to any claim.